


Sample Name: Poly(n-butyl methacrylate)

Sample #: P9634-nBuMA

**Structure:**




**Composition:**

| $M_n \times 10^3$        | PDI  |
|--------------------------|------|
| 14.0                     | 1.08 |
| $T_g (^{\circ}\text{C})$ | 30   |

**Synthesis Procedure:**

Poly(n-butyl methacrylate) is obtained by living anionic polymerization of n-butyl methacrylate. The reaction scheme used for the polymer synthesis is shown below:



**Characterization:**


The molecular weight and polydispersity index (PDI) of Poly(n-butyl methacrylate) are obtained by size exclusion chromatography.

**Solubility:**

Poly(n-butyl methacrylate) is soluble in THF,  $\text{CHCl}_3$ , toluene and dioxane. The polymer precipitates from cold methanol and ethanol.

**SEC of Homopolymer:**


**P9634-nBuMA**



Size Exclusion Chromatography of Poly(n-butyl methacrylate):

$M_n = 14,000$ ,  $M_w = 15,100$   $PI = 1.08$

**DSC thermogram for the polymer:**



**References for further information:**

- (a) S. K. Varshney, R. Fayt, Ph. Teyssie, US Patent 5,629,393, 1997 (b) Ph. Bayard, R. Fayt, Ph. Teyssie and S. K. Varshney, Vuillemin B, Phillipe, H, US patent 5,677,387, 1997. (c) Ph. Bayard, R. Fayt, Ph. Teyssie and S. K. Varshney, B. Vuillemin, H. Phillipe, US patent 5,687,534, 1997. (d) S. K. Varshney, R. Fayt, Ph. Teyssie, US Patent 5,723,559, 1998. (e) Ph. Teyssie, S. K. Varshney, R. Jerome, R. Fayt US patent, 4,826,941., 1989.
- Ph. Teyssie, Ph. Bayard, R. Jerome, S. K. Varshney, and J. S. Wang, *35th IUPAC International Union of Pure & Applied Chemistry International Symposium on Macromolecules* 1994, 67.
- Ph. Teyssie, R. Fayt, J. P. Hautekeer, C. Jacobs, R. Jerome, L. Leemans and S. K. Varshney *Makromolekular Chemie, Macromol. Symp.*, 1990, 32, 61-73.
- S. K. Varshney, J. P. Hautekeer, R. Fayt, R. Jerome, and Ph. Teyssie *Macromolecules*, 1990, 23, 2618-2622.