





SEC elugram of MMA-nBuMA [first block] in DMF:



Sample	Mn	Mw	Mp	Mw/Mn	IV
P40196-1_01.vdt	22,470	23,137	20,766	1.030	0.1276

SEC elugram of MManBuMA-b-HEMATMS [protected diblock copolymer] in DMF:



Sample	Mn	Mw	Mp	Mw/Mn	IV
P40196-2_01.vdt	58,944	64,831	58,342	1.100	0.2634

DSC thermogram of MManBuMA-b-HEMA diblock copolymer (2<sup>nd</sup> heating scan, 10°C/min):

