


Sample Name: Poly isoprene
(rich in 1,4 microstructure)

Sample #: P9390A-IP Tetramer

Structure:



Composition:

Mn x 10 ³	PDI
0.326	1.10

Synthesis:

The product was synthesized by anionic polymerization process using Sec. Butyl lithium initiator.

Characterization:

The product was characterized by ¹H NMR.

HNMR of the product:

