


Sample Name: Poly(styrene), ω -(secondary)bromo-terminated

Sample #: P41874-SBr

Structure:




Composition:

$M_n \times 10^3$	PDI
5.0	1.2

Synthesis Procedure:

Bromo terminated polystyrene was prepared by controlled radical polymerization process.




Characterization:

The molecular weight and polydispersity index of this polymer were determined by size exclusion chromatography (SEC) using a Varian liquid chromatograph equipped with a UV and refractive index detector. Polymer functionality was verified by FTIR/H NMR depending on the molecular weights. Furthermore, the quantitative yield of the end functionalization was also proven in the extinction of the polymer in the ATRP process to synthesize different di-block copolymers.

Solubility:

Polymer is soluble in THF, $CHCl_3$ and toluene. It is precipitated out from methanol, ethanol, hexane, and ether.

HNMR spectrum of the polymer:




SEC elugram of the Sample:

Agilent GPC/SEC Software

P41874-SBr

Chromatogram Plot



Molecular Weight Averages

Peak	Mp (g/mol)	Mn (g/mol)	Mw (g/mol)	Mz (g/mol)	Mz+1 (g/mol)	Mv (g/mol)	PD
Peak 1	6094	5221	6365	7948	11216	7460	1.219