


Sample Name: **Poly (2-Metoxy ethylacrylate)**

Sample #: **P43019D-2MeOEA**

Structure:



Composition:

Mn x 10 ³	PDI
352.0	2.0


Synthesis Procedure:

The polymer was synthesized by GTP process.

Characterization:

The product was characterized by size exclusion chromatography (SEC) and ¹H NMR.

¹H-NMR spectrum of the Polymer:



SEC elugram of the sample:

