


**Sample Name: Poly(methyl acrylate)**

**Sample #: P43041-MA**

**Structure:**



**Composition:**

Mn x 10 <sup>3</sup>	PDI
4.8	1.22


**Synthesis Procedure:**

The polymer was synthesized by GTP polymerization.

**Characterization:**

The polymer was characterized by size exclusion chromatography (SEC).

**SEC profile of the Sample:**



Molecular Weight Averages							
Peak	Mp (g/mol)	Mn (g/mol)	Mw (g/mol)	Mz (g/mol)	Mz+1 (g/mol)	Mv (g/mol)	PD
Peak 1	6231	4789	5840	7009	8172	6766	1.227