


Sample Name: Poly(methyl acrylate)

Sample #: P43041B-MA

Structure:



Composition:

Mn x 10 ³	PDI
3.4	1.19

Synthesis Procedure:

The polymer was synthesized by GTP polymerization.


Characterization:

The polymer was characterized by size exclusion chromatography (SEC).

SEC profile of the Sample:

P43041B-MA

Chromatogram Plot



Molecular Weight Averages

Peak	Mp (g/mol)	Mn (g/mol)	Mw (g/mol)	Mz (g/mol)	Mz+1 (g/mol)	Mv (g/mol)	PD
Peak 1	3970	3395	4049	4752	5466	4486	1.193