


Sample Name: Poly(methyl acrylate)

Sample #: P43041C-MA

Structure:



Composition:

Mn x 10 ³	PDI
14.0	1.08


Synthesis Procedure:

The polymer was synthesized by GTP polymerization.

Characterization:

The polymer was characterized by size exclusion chromatography (SEC).

SEC profile of the Sample:



Molecular Weight Averages							
Peak	Mp (g/mol)	Mn (g/mol)	Mw (g/mol)	Mz (g/mol)	Mz+1 (g/mol)	Mv (g/mol)	PD
Peak 1	14785	14112	15324	16607	17922	18170	1.088