


Sample Name: Hydroxy Terminated Polybutadiene, 1,2/1,4-microstructure

Sample #: P43224-BdOH

Structure:



Composition:

Mn x 10 ³	2.5
PDI	1.01


1,2-microstructure	90%
1,4-microstructure	10%

Synthesis Procedure:


OH-terminated polybutadiene was prepared by anionic living polymerization of butadiene in non-polar solvent followed by termination with ethylene oxide.

Characterization:


The product was characterized by size exclusion chromatography (SEC) and ¹HNMR.



¹HNMR spectrum of the Sample:



SEC elugram of the Sample:



Peak	Mp (g/mol)	Mn (g/mol)	Mw (g/mol)	Mz (g/mol)	Mz+1 (g/mol)	Mv (g/mol)	PD
Peak 1	2577	2511	2525	2538	2550	2533	1.008

Solubility:

Polymer is soluble in DMF, THF, toluene, hexane, cyclohexane and CHCl₃.