


**Sample Name: Poly(N-isopropyl acrylamide),
 α -Amino Terminated**

Sample #: P60691-23-NIPAMNH2

Structure:




Composition:

$M_n \times 10^3$	PDI
231.0	1.31

Synthesis Procedure:

Amino Terminated Poly(N-isopropyl acrylamide) was prepared by free-radical polymerization of N-isopropyl acrylamide in the presence of an amino group containing chain-transfer agent. The final polymer was purified by fractionation. The scheme of the reaction is illustrated below:




Characterization:

GPC-SEC experiments for MW and polydispersity determination, were performed on Agilent or Malvern tri-detector systems, equipped with a refractive index, viscometer and light-scattering detectors and a set of two or three Supelco columns. DMF, with up to 0.02M of LiBr, was used as a mobile phase.

Solubility:

The polymer is soluble in water, THF, CHCl_3 and CH_2Cl_2 , insoluble in hexane and ether.

SEC profile of the Sample:



Dn/dc value used: 0.077 mL/g