


**Sample Name: Poly(N-isopropyl acrylamide),
α-Amino Terminated**

Sample #: P60691-24-NIPAMNH2

Structure:




Composition:

Mn x 10 ³	PDI
129.2	1.38

Synthesis Procedure:

Amino Terminated Poly(N-isopropyl acrylamide) was prepared by free-radical polymerization of N-isopropyl acrylamide in the presence of an amino group containing chain-transfer agent. The final polymer was purified by fractionation. The scheme of the reaction is illustrated below:




Characterization:

GPC-SEC experiments for MW and polydispersity determination, were performed on Agilent or Malvern tri-detector systems, equipped with a refractive index, viscometer and light-scattering detectors and a set of two or three Supelco columns. DMF, with up to 0.02M of LiBr, was used as a mobile phase.

Solubility:

The polymer is soluble in water, THF, CHCl₃ and CH₂Cl₂, insoluble in hexane and ether.

SEC profile of the Sample:



Dn/dc value used: 0.077 mL/g