


Sample Name: Poly(ethylene oxide)-b-Poly(isopropyl methacrylate)

Sample #: P43957-EOisoPrMA

Structure:




Composition:

Mn x 10 ³ PEO-b-IsoPrMA	PDI
5.0-b-7.0	1.22

Synthesis Procedure:

Poly(Ethylene oxide- isopropyl methacrylate) is prepared as shown in the scheme below:




Characterization:

Polymer composition was determined by ¹H NMR taking the integration of PEG block at 3.66 ppm and methyl ester of PMMA block at 3.62 ppm. Molecular weights of the first block and the Mw/Mn of the final and the first block was determined by SEC in THF.

Solubility:

Poly(ethylene oxide -b- isoPrMA) is soluble in CHCl₃, THF, toluene. The polymer precipitated out from hexane.

¹H-NMR Spectrum of the block copolymer:



SEC of the block copolymer:

