


Sample Name: Deuterated Polybutadiene- d_6 (predominantly 1,4-addition), protonated end-groups.

Sample #: P42213C-R-dBd

Structure:




Composition:

$M_n \times 10^3$	M_w/M_n
390.0	1.6

Synthesis Procedure:

Deuterated polybutadiene- d_6 was obtained by living anionic polymerization of butadiene- d_6 monomer:




Characterization:

The molecular weight and polydispersity index (M_w/M_n) of the deuterated poly butadiene are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors from Viscotek Co. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used.


Solubility:

Polymer is soluble in toluene, THF and CHCl_3 .

H NMR spectrum of the Sample:



D NMR spectrum of the Sample:



SEC elugram of the polymer:

