


Sample Name: Poly(N-vinyl imidazole)

Sample #: P44555-VIMDZ

Structure:



Composition:

$M_n \times 10^3$	PDI
23.0	2.5

Synthesis Procedure:

Polymer is obtained by free radical polymerization using AIBN as free radical initiator.

Characterization:

The molecular weight and polydispersity index (PDI) of polymer is obtained by size exclusion chromatography in aqueous system (water as eluent with 0.1% trifluoroacetic acid and 0.2M NaCl). The columns were calibrated with polyethylene glycol.


Thermal analysis

Thermal analysis of the samples was carried out on a TA Q100 differential scanning calorimeter at a heating rate of 10°C/min. The midpoint of the slope change of the heat flow plot of the second heating scan was considered as the glass transition temperature (T_g).

Solubility:

Polymer is soluble in water, methanol and precipitated out from hexane, ether.

H NMR spectrum of the Sample:



SEC profile of Homopolymer:

