


# Product Profile

## Identification

**Product Name:** Amino Terminated Polystyrene

**Product Lot Number:** P44602B-SNH2

**Product Chemical Architecture:**




## Composition:

Mn x 10 <sup>3</sup>	Mw/Mn (PDI)	Microstructure of Polymer by <sup>1</sup> H NMR
128.0	1.65	Atactic
NH2 functionality > 99%		

## Method of Synthesis: Description of Synthesis

$\omega$ -amino terminated polystyrene was synthesized by anionic living polymerization with different end-grouping strategies. The reaction schemes are shown below:




## solubility in different solvents

THF	✓		
CHCl <sub>3</sub>	✓	CHCl <sub>3</sub>	✓
Toluene	✓		

## Validation of Architecture:

### A. Gel Permeation Chromatography (GPC), SEC- Profile



**Ref:** for details

Synthesis of Asymmetric Telechelic Polymers Bearing a Primary Amino End Group SUNIL K. VARSHNEY,1 ZHENGJI SONG,1 JIAN XIN ZHANG,1 ROBERT JEROME

Journal of Polymer Science: Part A: Polymer Chemistry, Vol. 44, 3400–3405 (2006)