


Sample Name:
Amino Terminated Polystyrene


Sample #: P1488-SNH2

This has architecture # 1.


Structure 1:



Structure 2:



Structure 3:






Composition:

Mn x 10 ³	PDI
12.0	1.02

Synthesis Procedure:

α , ω -amino terminated polystyrene was synthesized by anionic living polymerization with different end-grouping strategies. The reaction schemes are shown below:




Characterization:

The molecular weight and polydispersity index of this polymer were determined by size exclusion chromatography (SEC) using a Varian liquid chromatograph equipped with a UV and refractive index detector. However, amino terminated polystyrene was found to interact with chromatography columns and therefore the amino group was protected by reaction with 1-naphthyl isocyanate before GPC analysis. Removal of the protecting group was confirmed by UV spectroscopy and the degree of functionality was confirmed by titration with HClO₄ using crystal violet as the indicator.

Solubility: Polymer is soluble in THF, CHCl₃ toluene and precipitated out from methanol, hexane.

SEC of Sample:

P1488-NH2



Size exclusion chromatography of Amino Terminated polystyrene:

M_n=12000, M_w=12300, M_z=12600, PI=1.02, functionality>0.95