


Sample Name: Hydroxy Terminated

Polybutadiene, 1,2-rich microstructure

Sample #: P18311-BdOH

Structure:




Composition:

$M_n \times 10^3$	PDI	1,2 addition
17.5	1.06	>90%

Synthesis Procedure:

1,2-rich microstructure addition hydroxy terminated polybutadiene was prepared by anionic living polymerization of butadiene in polar solvent such as THF at 0 °C followed by termination with ethylene oxide. The scheme of the reaction is illustrated below:



Characterization:


The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co.

Functionality: functionality of the obtained polymer was determined by reacting polymer in dried non quantity of acetic anhydride in the presence of pyridine as a catalyst and the liberated COOH was titrated by acid-base titration.

Solubility:

Hydroxy terminated polybutadiene is soluble in DMF, THF, toluene, hexane, cyclohexane and CHCl_3 . It precipitates from methanol, ethanol and water.


^1H NMR of the Product:



SEC of Sample:

Sample ID: P18311-BdOH

Concentration (mg/mL)	3.7323
Sample dn/dc (mL/g)	0.1100
Method File	PS80K-NOV25-2013-0000.vcm
Column Set	3x PL 1113-6300
System	System 1



Sample	M_n	M_w	M_p	M_w/M_n	IV
P18311_01.vdt	17,549	18,704	19,232	1.066	0.3608

