


**Sample Name: Polybutadiene**  
**(rich in 1,2 microstructure)**  
**(1,2=65% , 1,4 = 35%)**

**Sample #: P18396-Bd**




**Composition:**


$\text{Mn} \times 10^3$	PDI
0.35	1.10

### Synthesis Procedure:




Polybutadiene (1,2-rich) is obtained by living anionic polymerization in THF. Using  $\text{Sec. BuLi}$  initiator.



Cis 1,4 addition



Trans 1,4 addition



### Characterization:

The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co.

Polymer microstructure can be confirmed by  $^1\text{H}$ -NMR where the spectrum of 1,2-polybutadiene

contains of 1 vinylic proton signal at 5.4 ppm and 2 vinylic protons at 5.0 ppm but the spectrum of 1,4-polybutadiene only contains vinylic signals at 5.4 ppm.

