



Sample Name: Deuterated Multiarm Polystyrene
Sample # P18522A-12dPS
12- arms Deuterated Poly styrene




Mn x 10 ³ (total)	PDI
12.0	1.16
Mn of each arm: (1.1)	

Synthesis Procedure:




Linker : Lot# P18516: Value of X 4 to 5 as average Mn 1100



SEC of the Polymer: (eah branch of Polystyrene)

Sample ID: P18522A-dPs Star

Concentration (mg/mL)	1.9908
Sample dn/dc (mL/g)	0.1700
Method File	PS80K-Feb25-2014-0000.vcm
Column Set	3x PL 1113-6300
System	System 1



Sample	Mn	Mw	Mp	Mw/Mn	IV
P18522A-dPS_star_01(179).vdt	11,782	13,719	13,522	1.164	0.1013

