


Sample Name: Deuterated Multiarm Polystyrene

Sample # P18522C-10dPS

10- arm Deuterated Polystyrene


Structure:



Composition:


Mn x 10 ³ (total)	Mn x 10 ³ (each arm)	Mw/Mn
11.8	1.1	1.10

Synthesis procedure:



Linker: Lot # P18516


Value of X: 4 to 5 (average Mn: 1100)



SEC elugram of the product:

Sample ID: P18522C-dPS Star

Concentration (mg/mL)	3.7804
Sample dn/dc (mL/g)	0.1850
Method File	PS80K-Feb25-2014-0000.vcm
Column Set	3x PL 1113-6300
System	System 1



Sample	Mn	Mw	Mp	Mw/Mn	IV
P18522C-dPS_star_01.vdt	11,849	13,124	12,645	1.108	0.1075

