



Sample Name: Complete Deuterated Multiarm
Polystyrene ;
Sample # P18572-25dPS


25-arm deuterated d3 Polystyrene



Concentration (mg/mL)	11.3285
Sample dn/dc (mL/g)	0.1700
Method File	PS80K-Feb25-2014-0000.vcm
Column Set	3x PL 1113-6300
System	System 1




Sample	Mn	Mw	Mp	Mw/Mn	IV
P18572-1_dPs_Branch_01.vdt	784	974	848	1.242	0.0591




Sample ID: P18572-dPS star

Concentration (mg/mL)	7.3507
Sample dn/dc (mL/g)	0.1700
Method File	PS80K-March13-2014-0000.vcm
Column Set	3x PL 1113-6300
System	System 1



Sample	Mn	Mw	Mp	Mw/Mn	IV
P18572-dPS_star_01(224).vdt	20,430	28,088	19,712	1.375	0.1224



Synthesis Procedure:

