



Sample Name: Complete Deuterated Graft
Polystyrene ;
Sample # P18644-44dPS

44- arms grafted Deuterated Poly styrene on
Deuterated poly butadiene back bone




Linker : Lot# P18531
SEC of the Polymer: (eah branch of Polystyrene)
Sample ID: P18644-dPS Branch


Concentration (mg/mL)	7.9698
Sample dn/dc (mL/g)	0.1100
Method File	PSS0K-Micro-17-2014-0000.ucm
Column Set	3x PL 1113-6300
System	System 1



Sample	Mn	Mw	Mp	Mw/Mn	PDI
DpS_Basic_01(87).udt	1,378	1,514	1,418	1.099	0.0313



Concentration (mg/mL)	17.7158
Sample dn/dc (mL/g)	0.1100
Method File	PSS0K-Micro-17-2014-0000.ucm
Column Set	3x PL 1113-6300
System	System 1



Sample	Mn	Mw	Mp	Mw/Mn	PDI
dps_star_01(95).udt	61,756	67,205	66,959	1.088	0.0495

