


**Sample Name:**


Hydroxy Terminated Poly(2-Vinyl Pyridine)

**Sample #:** P19129-2VPOH**Structure:****Composition:**

$M_n \times 10^3$	PDI
17.0	1.10
Functionality %	>99%
$T_g$ for the functional polymer	77°C

**Synthesis Procedure:**

Hydroxy terminated poly(2-vinyl pyridine) was prepared by living anionic polymerization of 2-vinyl pyridine in THF using OH protected initiator. The scheme of the reaction is illustrated below:

**Characterization:**

The molecular weight and polydispersity index of this polymer were determined by size exclusion chromatography (SEC) using a Varian liquid chromatograph equipped with a UV and refractive index detector.

**Thermal analysis:**


Thermal analysis of the samples was carried out using a differential scanning calorimeter (TA Q100) at a heating rate of 10°C/min. The inflection glass transition temperature ( $T_g$ ) has been considered.

**Solubility:**

Polymer is soluble in  $\text{CHCl}_3$  and THF.

**SEC of Sample:****Sample ID:** P19129-2VPOH

Concentration (mg/mL)	2.4096
Sample dn/dc (mL/g)	0.1670
Method File	PS80K-Feb26-2015-0000.vcm
Column Set	3x PL 1113-6300
Solvent	THF



Sample	MW Number Average (Da)	MW Weight Average (Da)	MW at Peak (Da)	Polydispersity	Intrinsic Viscosity (dL/g)
Test_01(488).vdt	17,190	18,966	18,492	1.105	0.2774

**DSC thermogram for the sample:**