


Sample Name: Poly(4-chloro styrene)

Sample #: P19635-4CIS

Structure:




Composition:

Mn x 10 ³	PDI
219.0	1.3

Synthesis Procedure:

Poly(4-chloro styrene) is synthesized by free radical polymerization of 4-chloro styrene and the reaction scheme is shown below.



Characterization:

The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC).


Solubility:

Poly(4-chloro styrene) is soluble in DMF, THF, toluene and CHCl₃. It precipitates from methanol, ethanol, water and hexanes.

SEC of Homopolymer:

Sample ID-P19635-4CIS

Concentration (mg/mL)	0.5165
Sample dn/dc (mL/g)	0.1850
Method File	PS80K-June30-2015-0000.vcm
Column Set	3x PL 1113-6300
Solvent	THF



Sample	MW Number Average (Da)	MW Weight Average (Da)	MW at Peak (Da)	Polydispersity	Intrinsic Viscosity (dL/g)
P19635_01.vcl	219,388	299,286	118,625	1.319	3.0503