


sample Name:

Poly(ethylene oxide -b- styrene-co-4vinylpyridine)random copolymer

Sample #: P10215-EOS4VPran

Structure:



Composition:

Mn x 10 ³ PEO-b-S4VP	PDI
5.0-b-20.0	1.25
S:4VP ratio 15:85	

Characterization:


An aliquot of the anionic poly(ethylene oxide) block was terminated before addition of lactide and analyzed by size exclusion chromatography (SEC) to obtain the molecular weight and polydispersity index (PDI). The final block copolymer composition was calculated from ¹H-NMR spectroscopy.

Solubility:

The polymer is soluble in chloroform, DMF, methanol and precipitates from, ether and hexane.

SEC of the block copolymer:

P10215-EO-S4VPran



Size exclusion chromatography of the polymer carried out in DMF:

- mPEG Mn=5000, Mw=5,200, PI=1.05
- - - Block Copolymer EO(5,000)-b-S4VPran (20,000), PI=1.25

HNMR of the Polymer:

