


Sample Name:


**Sulfonic Acid Terminated Polystyrene**

Sample #: **P2252-SSO3H**

Structure:



or



Composition:

Mn x 10 <sup>3</sup>	PDI
2.1	1.40
T <sub>g</sub> (°C)	74

### Synthesis Procedure:

Sulfonic acid functionalized polystyrene was prepared by living anionic polymerization of styrene followed by termination with dried propansultone. Salts of this polymer were prepared by neutralization with the base solution.

### Characterization:

The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors. The molecular weights and the polydispersity index for the precursor (pick-out before propansultone addition) polymer were calculated. The functionality of polymer was verified by proton NMR for a low molecular weight and by acid base titration for high molecular weights polymer.

### Thermal analysis:


Thermal analysis of the samples was carried out using a differential scanning calorimeter (TA Q100) at a heating rate of 10°C/min. The inflection glass transition temperature (T<sub>g</sub>) has been considered.

### Solubility:

Polymer is soluble in DMF, THF, toluene and CHCl<sub>3</sub>. It precipitates from cold methanol, ethanol, water and hexanes.

### SEC of Sample:

**P2252-SSO3H**



Size exclusion chromatograph of Poly styrene before termination with propansultone:

Mn 2100 Mw: 3000 PI: 1.40

### DSC thermogram for the polymer:

