


Sample Name:  
**Six-Arm Poly(ethylene oxide) Hydroxy  
 Terminated\*, Dipentaerythritol Core**


**Sample #: P3169A-6EOOH**



$M_n \times 10^3$ (total)	PDI
11.0	1.3

**Synthesis Procedure:**

The polymer was prepared by anionic living polymerization of ethylene oxide using dipenta erythritol potassium salt or other hexa functional compound as the initiator. The scheme of the reaction is illustrated below:



**Characterization.**

By Size exclusion chromatography (SEC): Varian liquid chromatograph equipped with UV and refractive detector. SEC columns from Supelco were used with THF containing 2 vol% (Et)<sub>3</sub>N as the eluent. The molecular weights were determined using light scattering detector and viscosity detector. The molecular weights and the polydispersity indice were calculated.

An aqueous GPC column from Supelco(G5000 PWXL) was also used with 0.5 M acetic acid and 0.8 M NaNO<sub>3</sub> as the eluent. It was kept at a constant temperature of 50°C. The flow rate was 1.0 ml/min. The column was calibrated with monodisperse poly(ethylene oxide) standards. The molecular weights and the polydispersity index of polyethylene oxide were calculated by using a Visual Basic GPC software.

**Purification of the obtained polymer:**

Purification of the obtained polymer was carried out rigorously as follows to ensure the removal of the catalyst side product:


1. Dissolved the polymer in de-ionized distilled water to remove the any insoluble organic catalyst side product.

2. Polymer extracted from water with dichloromethane.
3. Polymer solution in dichloromethane was dried over anhydrous sodium sulfate.
4. Solution filtered and than passed through a column packed with basic Al<sub>2</sub>O<sub>3</sub>.
5. Solution concentrated on rota-evaporator
6. Solution precipitated in cold diethyl ether.
7. Dried under vacuum for 48h at 38 oC.

**Solubility:**


Polymer is soluble in toluene, THF, water and CHCl<sub>3</sub>. The polymer is insoluble in hexane, ether, cold isopropanol and ethanol.

HNMR of the Polymer Carried out in DMSO:



**SEC of the product**

**P3169A-6EOOH**



Size Exclusion Chromatogram of Six-Arm Poly(ethylene glycol)

— P3169:  $M_n=11000$ ,  $M_w=14300$ ,  $M_w/M_n=1.3$   
 intrinsic viscosity in THF at 30 oC 0.187dl/g dn/dc 0.052  
 radius of gyration: 5.01 nm.