



Sample Name:
Amino Terminated Polystyrene

Sample #: P4049-SNH2
This lot bears structure # 2


Structure 1:



Structure 2:



Structure 3:




Composition:

Mn × 10 ³	PDI
85.0	2.5
T _g (°C)	102

Synthesis Procedure:

α, ω-amino terminated polystyrene was synthesized by anionic living polymerization with different end-grouping strategies. The reaction schemes are shown below:



Characterization:

The molecular weight and polydispersity index of this polymer were determined by size exclusion chromatography (SEC) using a Varian liquid chromatograph equipped with a UV and refractive index detector. However, amino terminated polystyrene was found to interact with chromatography columns and therefore the amino group was protected by reaction with 1-naphthyl isocyanate before GPC analysis. Removal of the protecting group was confirmed by UV spectroscopy and the degree of functionality was confirmed by titration with HClO₄ using crystal violet as the indicator.


Thermal analysis:

Thermal analysis of the samples was carried out on a TA Q100 differential scanning calorimeter at a heating rate of 10°C/min. The midpoint of the slope change of the heat flow plot of the second heating scan was considered as the glass transition temperature (T_g).

Solubility: Polymer is soluble in THF, CHCl₃ toluene and precipitated out from methanol and hexane.

SEC of Sample:

P4049-SNH2



Size exclusion chromatography of Amino terminated polystyrene.
 (NH₂ group end capped with 1-naphthyl isocyanate)
 Mn 85,000 MW: 212,000 Mw/Mn:2.5