


### Sample Name:

Random Copolymer Poly(n-Butyl methacrylate-co-tert-butyl methacrylate)

Sample #: P5777-n-BuMAAtBuMA ran

### Structure:



### Composition:


Mn × 10 <sup>3</sup> PnBuMA-co-tert.BuMA	PDI
480.00	1.20
T <sub>g</sub> of random polymer	42 °C
nBuMA:tBuMA ratio	90:10
Syndio:hetero:iso fraction	77:21:2

### Synthesis Procedure:

Random Copolymer Poly(n-Butylmethacrylate-co-tert.butyl methacrylate) is prepared by anionic polymerization.

### Characterization:

The polymer was analyzed by size exclusion chromatography (SEC) to obtain the molecular weight and polydispersity index (PDI). The copolymer composition was calculated from <sup>1</sup>H-NMR spectroscopy by comparing the peak area of the protons of methylene (-CH<sub>2</sub>) of nBuMA at 4ppm and tert.butyl of tert.BuMA at about 1.4 ppm. Following are the estimated chemical shifts:




### Thermal analysis

Thermal analysis of the samples was carried out on a TA Q100 differential scanning calorimeter at a heating rate of 10°C/min. The midpoint of the slope change of the heat flow plot of the second heating scan was considered as the glass transition temperature (T<sub>g</sub>).


### Solubility:

The polymer is soluble in CHCl<sub>3</sub>, THF, DMF, toluene and precipitated out from methanol and water.

### <sup>1</sup>H-NMR Spectrum of the random copolymer:



### SEC of the random copolymer:



### Size Exclusion Chromatography of Copolymer:

M<sub>n</sub> = 480,000, M<sub>w</sub> = 576,000, M<sub>w</sub>/M<sub>n</sub> = 1.20  
Solution Viscosity in THF at 35 °C: 1.468 dl/g  
dn/dc in THF at 35 °C: 0.084 ml/g  
R<sub>gw</sub>: 28.90 nm

### Thermogram for the sample:

