


Sample Name: Poly(ethylene glycol) or hexa(methylene)glycol

Sample #: P5798-EG2OH (hexamer)

Structure:




#### Composition:

Mn x 10 <sup>3</sup>	PDI
0.282	1.03

#### Synthesis Procedure:

Poly (ethylene glycol) is obtained by living anionic polymerization and the reaction. Scheme of the polymerization is illustrated below:



	Initiator System	Resulting Polymer
1)	$\text{CH}_3\text{OCH}_2\text{CH}(\text{CH}_3)\text{OK}$	polyethylene glycol methyl ether
2)	$\text{CH}_3\text{OCH}_2\text{CH}(\text{CH}_3)\text{OK}$	$\alpha, \omega$ -term. methyl ether polyethylene glycol
3)	$\text{KOCH}_2\text{CH}_2\text{OK}$	polyethylene glycol
4)	$\text{CH}(\text{C}_5\text{H}_6)_2\text{CK}$	polyethylene glycol diphenyl ether
5)	$(\text{CH}_3)_2\text{N}-\text{CH}_2\text{CH}_2\text{OK}$	methyl amino terminated PEG
6)	$(\text{CH}_3)_2\text{N}-\text{CH}_2\text{CH}_2\text{OK}$	$\alpha$ -methyl amino $\omega$ -methyl ether term. PEG

#### Characterization:

By Size exclusion chromatography (SEC): Varian liquid chromatograph equipped with UV and refractive detector. SEC columns from Supelco were used with THF containing 2 vol%  $(\text{Et})_3\text{N}$  as the eluent. The molecular weights were determined using light scattering detector and viscosity detector. The molecular weights and the polydispersity indice were calculated.

An aqueous GPC column from Supelco(G5000 PWXL) was also used with 0.5 M acetic acid and 0.8 M  $\text{NaNO}_3$  as the eluent. It was kept at a constant temperature of 50°C. The flow rate was 1.0 ml/min. The column was calibrated with monodisperse poly(ethylene oxide) standards. The molecular weights and the polydispersity index of polyethylene oxide were calculated by using a Visual Basic GPC software.

#### Purification of the obtained polymer:

Purification of the obtained polymer was carried out rigorously as follows to ensure the removal of the catalyst side product:


1. Dissolved the polymer in de-ionized distilled water to remove the any insoluble organic catalyst side product.
2. Polymer was extracted from water with dichloromethane.
3. Polymer solution in dichloromethane was dried over anhydrous sodium sulfate.
4. Solution was filtered and then passed through a column packed with basic  $\text{Al}_2\text{O}_3$ .
5. Solution was concentrated on rota-evaporator
6. Solution was precipitated in cold diethyl ether.
7. Dried under vacuum for 48h at 38 oC.

#### Solubility:

Poly(ethyl glycol) is soluble in toluene, THF, water and  $\text{CHCl}_3$ . The polymer is insoluble in hexane, ether, cold isopropanol and ethanol.

#### SEC of Sample of the polymer

**P5798A-EG2OH (hexamer)**



Size exclusion chromatograph of Hexa (methylene )glycol  
 $M_n=282$ ,  $M_w/M_n=1.03$