


Sample Name: Poly(4-bromo styrene)

**SEC of Homopolymer:
P5850-4BrS**

Sample #: P5850-4BrS

Structure:




Composition:

$M_n \times 10^3$	PDI
24.0	1.4

Synthesis Procedure:

Poly(4-bromo styrene) is synthesized by free radical polymerization of 4-bromo styrene and the reaction scheme is shown below.




Characterization:

The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography.

Solubility:

Poly(4-bromo styrene) is soluble in DMF, THF, toluene and CHCl_3 . It precipitates from methanol, ethanol, water and hexanes.



Size Exclusion Chromatogram of poly 4-bromo styrene:
— $M_n=24000$, $M_w=33,500$, $M_w/M_n=1.4$