


**Sample Name:**  $\alpha, \omega$ -Dithiol terminated Poly(N-isopropyl acrylamide)

**Sample #:** P6697-NIPAM2SH

**Structure:**




**Composition:**

Mn x 10 <sup>3</sup>	PDI
4.0	1.15

**Synthesis Procedure:**

The polymer was prepared by reversible addition-fragmentation chain transfer polymerization (RAFT) of N-isopropyl acrylamide. The scheme of the reaction is illustrated below:



**Purification of polymer:**

Unreacted monomer was removed by dissolving the product in cold water than warming up the solution. The polymer separated out. This procedure was applied 2 times to remove the unreacted monomer. The obtained polymer was dissolved in acetone and reprecipitated in cold ether.

**Hydrolysis of the Trithiocarbonate End Groups in Poly(NIPAM-SH).** The TTS end groups of the obtained polymer samples were hydrolyzed to yield the corresponding thiol-terminated polymers under basic conditions. For this purpose, the polymer was dissolved in a mixture of MeOH/aq. 28% NaOH (2:1) and stirred under nitrogen overnight. The reaction mixture was acidified with 88% formic acid, MeOH was evaporated and the residue was dissolved filter and then precipitated in cold diethyl ether.


**Characterization:**

Size exclusion chromatography (SEC) was carried out on a Varian liquid chromatograph equipped with a refractive index detector. A Shodex 806L GPC columns from Supelco was used with DMF(0.05M LiBr) as the eluent and also in THF following the procedure as out lined in **Macromolecules, 2000,33,6738**. To avoid the effect of concentration and the amount of water present in the sample, on line triple detectors were used and the dn/dc was calculated and found : 0.104mL/g in THF at 35 oC The columns were calibrated with monodisperse polystyrene standards. The polydispersity index was calculated. The molecular weight was calculated by NMR based on the initiator moiety.

**Solubility:**

The polymer is soluble in water methanol, ethanol, DMF, and dioxane, not soluble in hexane.

**HNMR of the RAFT reagent used:**



**SEC Profile of Polymer:**

